ZOOM

CG626

CARBON BRUSHES FOR WIND TURBINES

FOR PHASE AND GROUNDING OF WIND TURBINE GENERATORS

A PREMIUM GRADE

- Fitted to any wind generator
- Approved by most Original Equipment Manufacturers (OEM)*
- Already in operation in the world largest wind farms*

PRINCIPAL CHARACTERISTICS

- Low friction coefficient
- Minimal dusting
- Optimum performance in all environmental conditions

* Please contact us for our lists of references.

MERSEN PROPERTY

CG626 METAL-GRAPHITE GRADE FOR BRONZE AND STAINLESS-STEEL SLIP RINGS

- High current density capabilities (up to 18 A/cm^2)
- Proven grounding performance
- Offering extended life, even at high temperatures
- Lab and field-tested
- No aggressiveness towards the ring

Average physical characteristics:

- Bulk density: 2,9
- Resistivity: 180 µΩ.cm
- Flexural strength: 45 MPa
- Metal content: 49%
- Graphite and additives: 51%

Recommended running conditions:

- Current density: 12 - 18 A/cm²
- Peripheral speed: ≤ 40 m/s
- Pressure on carbon brush: 18 - 25 kPa

Peripheral speed: 30 m/s



Current density: 12 A/cm²



PTT-CG626-EN-2609

The specifications or data contained in the present document are only given for information and do not create any undertakings whatsoever. Any copy, reproduction or translation, either partially or fully, of this information is subject to the Mersen's prior written consent. In addition, due to the continuing improvement of techniques and change of applicable standards, Mersen is entitled to modify at any time the characteristics and specifications of its products as described in the present document.
Mersen products have been designed, manufactured and tested by Mersen for a range of specific industrial application to be operated depending on particular specification and climatic conditions.
BEFORE ordering, please contact Mersen. In order to ensure that the product is adequate and fits with your need you should contact/provide Mersen with all relevant technical specifications and climatic conditions. MERSEN makes no representation or/and warranty, and waives any liability, either express or implied for products' reliability and lifetime performance in case Mersen has not been provided with customers specifications or if the products are not purchased directly from MERSEN or its distributors and/or agents.

MERSEN PROPERTY

Contact: info.ptt@mersen.com